

Technical Data Sheet

AFN-09N

General Description

- Daylight and ultra-violet responsive fluorescent submicron dispersion - formaldehyde free - for water-based formulations.
- A dyed/pigmented dispersion of an alkali soluble acrylic resin.

Applications

- UV Blue tracer for water based inks for flexo, gravure and textile.
- UV Blue tracer for water based paper coatings and paints.

Product Features

- AFN-09N is relatively invisible in daylight, but produces a highly visible bright and vibrant blue color when exposed to ultra-violet.
- AFN-09N contains approximately 48% fluorescent pigment dispersed in water.
- AFN-09N is free of the following chemicals: Formaldehyde, Alkyl phenols (Ethoxylates), AZO compounds, Aromatic amines, SVHC Chemicals, Heavy Metals, Perfluorooctanoic Acid, Regulated Phthalates, Polyaromatic Hydrocarbons, Bisphenol A (BPA)
- For aqueous formulations, the use of preservatives is highly recommended. The right preservative package (combination of bactericides and fungicides) should provide reliable, highly effective control of micro-organisms in the intended formulation.

Standard Color

Product Name	Description
AFN-09N	UV Blue

Packaging:

1 HDPE jerry-can = 20kg
 1 drum = 200kg
 MOQ = 20kg

Storage & shelf life:

24 months after production date when kept in closed original packaging in a dry place at ambient temperatures. Dispersion should be protected from freezing.

Safety & regulatory:

Safety Data Sheet available on request.

Physical properties	
Delivery form	Liquid, 46-50% solids
Particle size (Laser diffraction)	± 0.25 – 0.45µm
Hegman grind	5.0 – 8.0
pH range	7.5 – 9
Specific gravity	1.0 – 1.1 g/ml
Brookfield viscosity	50 – 350 cps @ 25°C

Test methods and Certificate of Analysis (COA) available on request.

Processing

Solvent resistance	Water based product.
--------------------	----------------------

Adding AFN-09N will purify the color and increase the UV response.

AFN-09N dispersion is designed for use at industrial sites as described in EU COMMISSION REGULATION 2023/2055 of 25 September 2023.

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product.