



Technical Data Sheet

PAP

General Description

- Daylight and ultra-violet responsive fluorescent plastic colorants - free of formaldehyde - for the paper coating industry.
- A dyed/pigmented thermoplastic polyamide-ester resin.

Applications

 Recommended for extrusion, injection moulding, blow moulding, film blowing etc.

Product Features

- PAP offers bright colors for applications where safety and high visibility is required.
- PAP has no formaldehyde outgassing and is odorless during its transformation.
- PAP has the advantage of a low level of migration, whereby both heat stability and light resistance are optimized.
- For aqueous formulations, the use of preservatives is highly recommended. The right preservative package (combination of bactericides and fungicides) should provide reliable, highly effective control of microorganisms in the intended formulation.

Physical properties		
Delivery form	Powder	
Particle size (Laser diffraction)	8.0 – 15.0 µm	
Decomposition temp.	>300°C	
Specific gravity	1.20 g/ml	
Bulking value	0.3 – 0.4 g/ml	

⁽¹⁾ Test methods and Certificate of Analysis (COA) available on request.

Processing

PAP Fluorescent pigments are semi-transparent. For this reason printing on a white coated surface is recommended to obtain the maximal fluorescent effect.

Pigments are insoluble and need to be dispersed (easily stir-in).

Statidata Colors		
Product	Description	
Name		
PAP-3-0933	Orange	
Packaging:		
1 box = 20kg		
MOQ = 20kg		
Storage & shelf life:		
120 months when kept in closed		
original packaging in a dry place		
at ambient temperature.		
Safety & regulatory:		

Safety Data Sheet available on

request.

Standard Colors

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product. Rev:1.0 10-Jun-22