

Technical Data Sheet

QF – Quick Fading

General Description

- Daylight and ultra-violet responsive fluorescent pigments for temporary markings, suitable for use in water borne and solvent based formulations.
- A dyed/pigmented thermoset sulphonamide-melamine-paraformaldehyde resin.

Applications

- Temporary markings, sport events, clay pigeons.

Product Features

- QF is suitable for use in water borne formulations as well as applications where resistance to strong solvents and temperature is required.
- QF is especially developed for fast fading outdoor applications. They are stable to indoor light, but will fade quickly under outdoor conditions.
- For aqueous formulations, the use of preservatives is recommended. The right preservative package (combination of bactericides and fungicides) should provide reliable, highly effective control of microorganisms in the intended formulation.

Standard Colors

Product Name	Description
QF-23	Orange
QF-17	Pink
QF-19	Blue

Packaging:

1 box = 20kg (2x10kg)
 MOQ = 200kg

Storage & shelf life:

120 months when kept in closed original packaging in a dry place at ambient temperature.

Safety & regulatory:

Safety Data Sheet available on request.

Physical properties	
Delivery form	Powder
Particle size (Laser diffraction)	± 5.0 µm
Hegman grind	5.0 – 6.0
Melting point	Thermoset, non-melting
Decomposition temp.	>300°C
Specific gravity	1.38 – 1.40 g/ml
Bulking value	0.25 g/ml
Oil absorption	56

(1) Test methods and Certificate of Analysis (COA) available on request.

Processing	
Heat stability	Applications with processing temperature up to 180°C.
Solvent resistance	Recommended use in water, aliphatic- and aromatic hydrocarbons, alcohols, esters, glycols, plasticizers.
Pigments are insoluble and need to be dispersed (easily stir-in).	

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product.