

Technical Data Sheet

RBU

General Description

- Daylight and ultra-violet responsive fluorescent ink base, free of formaldehyde for energy curable inks.
- A high strength fluorescent formulation in a specifically formulated ink vehicle.

Applications

- Flexographic and lithographic, ultra-violet (UV) and electron beam (EB) curable inks.

Product Features

- High fluorescent ink base which needs to be converted into finished flexographic and lithographic UV curable inks by adding specific resins and a photo initiator.
- Bright and high gloss colors, covering the PMS shades from 802 to 807, with excellent printing characteristics.
- Compatible with conventional inks to enlarge the available color space to create new and brighter shades.
- RBU ink base contains reactive components. Therefore during the manufacturing of these printing inks the temperature of the batch should not exceed 40°C. For additional information on safe handling procedures, please consult the individual Safety Data Sheets.

Standard Color

| Product Name | Description |
|----------------|-------------|
| RBU-10 | Chartreuse |
| Special Colors | |
| RBU-1P2 | Green |
| RBU-0P3 | Yellow |
| RBU-3P4 | Orange |
| RBU-5P5 | Red |
| RBU-7P6 | Pink |
| RBU-8P7 | Magenta |

Packaging:

1 PE pail = 20kg
MOQ = 20kg

Storage & shelf life:

12 months when kept in closed original packaging in a dry place at ambient temperature.

Safety & regulatory:

Safety Data Sheet available on request.

Physical properties

| | |
|----------------------------|------------------------------------|
| Delivery form | Ink base |
| Pigment concentration | 45-55 % thermoplastic dyed polymer |
| Vehicle type | Proprietary energy curable system |
| Grind – NPIRI 10-0 | 0 – 10 |
| Dirt-NPIRI 10-0 | 0 – 10 |
| Specific gravity | 1.20 g/ml |
| Laray viscosity | 20 – 40 seconds @ 32°C (200g/10cm) |
| Volatile organic compounds | None |

(1)Test methods and Certificate of Analysis (COA) available on request.

Processing

| | |
|------------------------|-------|
| Processing temperature | ≤40°C |
|------------------------|-------|

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product.